



PRODUCT DATA SHEET	Page 1 of 2
	Revision: 2 US
RD-ELASTOROOF	Date: 2/15/2007
	R3

DESCRIPTION OF THE PRODUCT

USE: Waterborne acrylic dispersion, single component waterproofing product for waterproofing or overcoating roofs.

FEATURES: Forming of a very elastic, durable – waterproof coating system – Permeable to vapours.

Note: RD-ELASTOROOF “dry-fall” characteristics help reduce the risk of overspray on buildings and surrounding property. Application methods include “dry-fall” under certain conditions (see Application).

SUBSTRATES: All substrates, if the appropriate system is applied. Do not apply on PVC roofing or on bituminous substrates that are less than one year old. Substrates include but are not limited to; EPDM, Modified Bitumen, BUR and most standard roofing insulations and recovery boards. Can also be applied directly to concrete, wood and tiles.

SYSTEM:

Porous, non treated surfaces:

- Primer: 1 coat RD-UNIFIX.
- Topcoat: 2 coats of RD-ELASTOROOF applied at 25 mils DFT each.

Ferrous and non-Ferrous metals:

- Primer: 1 coat of RD-ELASTOMETAL applied at 7-8 mils DFT.
- Topcoat: 2 coats of RD-ELASTOROOF applied at 25 mils DFT each.

Bituminous substrates older than one year:

- Direct application of 2 coats of RD-ELASTOROOF applied at 25 mils DFT each.

Note: On flat roofs, the product must be reinforced with mesh and a finishing coat of RD-ELASTOROOF ALU must be applied, (in place of the 2nd coat of RD-ELASTOROOF) at 25 mils DFT.

APPLICATION INSTRUCTIONS

PREPARATION OF THE SUBSTRATE: The substrate has to be clean, dry, and free of dust. In case of moss or mildew on the substrate, remove it with a special anti-moss product followed by pressure washing. Fill up cracks with RD-ACRYKIT caulking.

APPLICATION CONDITIONS: Environmental Conditions (general requirements).

- The minimum air and substrate temperatures; 45°F for 24 hours.
- The maximum surface temperature; 130°F.
- The maximum relative humidity; 90%.

Surface temperature must be at least 5°F above the Dew Point, with no threat of rain for 3 hours.

APPLICATION MEANS: Brush, roller or airless spray (tip size: 018–023).

Caution: Dry overspray can be wiped or washed from most surfaces. Satisfactory dry-fall performance depends upon height of work and equipment adjustment. Low temperature and high humidity are of particular concern. Test for application as follows: Spray from 15 to 25 feet towards paint container. The material then should readily wipe off.



PRODUCT DATA SHEET	Page 2 of 2
	Revision: 2 US
RD-ELASTOROOF	Date: 2/15/2007
	R3

Note: In some instances heat can fuse-dry overspray to some surfaces. Always clean dry overspray from hot surfaces before fusing occurs. Be aware that surface temperatures can be higher than air temperature.

DILUTION: Water (Only for airless spray: up to 3% during fast drying conditions.)

CLEANING OF TOOLS: Water.

COVERAGE: Theoretical Coverage / 25 KG Container

- 190 sq ft at 25 mils DFT.
- 95 sq ft at 50 mils DFT.

PARTICULARITIES: Mix before use.

TECHNICAL DATA

FINISH: Satin flat.

COLORS: Gray (standard) and other colors on request.

SOLIDS CONTENT : By weight: 72%.
By volume: 58%.

VOC CONTENT : 0 g/l.

DENSITY : Ca. 1.55.

FLASH POINT: Not flammable.

VISCOSITY: 150 - 200 P (Brookfield 20 Rpm).

DRYING TIME: 3 – 24 hours per coat, depending on temperature, humidity and wind.

PACKING: 5 KG – 25 KG.

STORAGE STABILITY: 2 years minimum provided the original container is sealed and has been stored in a controlled environment.

TEST DATA: Available upon request.

TEMPERATURE RESISTANCE: (Dry) Continuous 175° F.

SAFETY DATA

The Material Safety Data Sheet is available on request.

These specifications are given for information. Since the manufacturer is not able to check the correct application of the products, they cannot accept any responsibility for it. This technical data sheet replaces all previous editions.